Technical Data Sheet

SOLTECH®
WOOD & INDUSTRIAL COATINGS

311-0011

Premium ACYRLIC SANDING SEALER 5+1

Product Description	Alkyd resin and nitrcellulose based, air-drying, resistant to fading, excellent whiteness and hiding powered gloss paint that forms smooth and regular film.
Suggested Uses	Used as finishing paint in all wood or metal surfaces, whose surface is prepared with proper primers, of interior furnitures.
Application Equipments	Compatible with Airless and Airmix spray systems.
Color, Appearance	White
Solids Content (%)	30,00 ±2
Density (g/ml)	0,93± 0,20 (20 º C)
Gloss	60 º C 95-105 gloss
Viscosity	DINCUP-4 60-70 sc. at 20º C
Mixture Content	Varnish :100 Hardener : 20 Thinner : 20
Dry Time	to emery : 4 h (at 20ºC) to dry hard : 12 hour
Thinner	SOLTECH ® Cellulosic,Polyurethane or Acyrlic Thinner
Storage Conditions	Recommended to be stored in cool and dry places with proper ventilation and no direct sunlight exposure. Should be kept away from sources of fire and heat and necessary fire extinguishing measures should be taken.
Consumption (g/m²)	100-120 (for single coat)
Flas Point	-20 ºC
Package Type	10 Kg

Technical Consultancy, Application and Process: Verbal, written or practical solutions and recommendations given by our technical service regarding the use of the products are based on the experience and knowledge of our company and does not remove the testing responsibility of the user regarding his/her intended use and is not binding in a way to include the rights of the related third persons. Application, usage and process of the products happen outside of our control opportunity and the entire responsibility belongs to the user. While the responsibility of our company is not fully eliminated, it is limited with the value measure of the products rovided by us and consumed by the user. Needless to say, we guarantee the product continuance of all our products pursuant to our general sales and delivery conditions. New versions of this brochure override the previous ones. Please conform to EC safety forms

Aker Boya Kimya San. ve Tic. Ltd. Şti. BOSB 1.Cd. 6.Sk. No:3 34953 Tuzla – İstanbul / TURKEY P.+ 90 216 59317 00 F.+ 90 216 593 17 08
info@akerboya.com www.akerboya.com