

Technical Data Sheet

Printing date 01.06.2009
page 1/1

SOLTECH[®] PLUS CELLULOSIC BLACK PRIMER 552-9000

Product Description	: Alkyd resin based, air-drying, base coat colorant with high adherence and color intensity that forms regular textures thanks to its special thixotropic structure.
Suggested Uses	: Used for getting composite wood texture in cellulosic, polyurethane finishing painted or varnished surfaces of interior furnitures or to give worn appearance or depth to new works.
Application Equipments	: Brush, polishing cloth compatible with airless or airmix spray systems.
Color, Appearance	: Black, thixotropic liquid
Solids Content (%)	: 30 ± 2
Density (g/ml)	: 1,0 ± 0,20 (at 20 C°)
Gloss	: Flat
Viscosity	: DINCUP4 90 sec. (at 20 C°)
Dry Time	: To touch : 30 min. (20 C°), To dry hard : 6 hours (20 C°)
Thinner	: Soltech Plus synthetic thinner or naphtha, when necessary.
Storage Conditions	: Recommended to be stored in cool and and dry places with proper ventilation and no direct sunlight exposure. Should be kept away from sources of fire and heat and necessary fire extinguishing measures should be taken.
Consumption (g/m²)	: 50 – 60 depending on application method
Flash Point	: -4 °C
Package Type	: 13 Kg.

Technical Consultancy, Application and Process: Verbal, written or practical solutions and recommendations given by our technical service regarding the use of the products are based on the experience and knowledge of our company and does not remove the testing responsibility of the user regarding his/her intended use and is not binding in a way to include the rights of the related third persons. Application, usage and process of the products happen outside of our control opportunity and the entire responsibility belongs to the user. While the responsibility of our company is not fully eliminated, it is limited with the value measure of the products provided by us and consumed by the user. Needless to say, we guarantee the product continuance of all our products pursuant to our general sales and delivery conditions. New versions of this brochure override the previous ones. Please conform to EC safety forms.